



# Hot Rolled Steel



PRODUCT MANUAL

熱軋

 CHINASTEEL

## The quality policy of China Steel Corporation

China Steel Corporation, based-on customer orientation, will incessantly innovate, research & develop to provide excellent and eco-friendly products, and consequently fulfill our responsibility to society.



- 1 1. Brief Introduction  
2 2. Product and Service Features  
3 3. Introduction of New Products  
4 4. Certification  
5 5. Manufacturing Process and Major Equipments  
6 6. Application Examples  
10 7. Specification  
11 8. Product Availability  
34 9. Marking and Packing  
35 10. Precautions for Use  
36 11. Conversion Tables  
41 12. Comparison of Specification  
42 13. Ordering Information


A NAME FOR QUALITY,  
TECHNOLOGY AND SERVICE



 CHINASTEEL

China Steel Corporation (CSC), located at Kaohsiung, Taiwan was founded in December 1971. With annual capacity (in terms of crude steel) around 10 million tonnes, CSC produces a range of products that includes plates, bars, wire rods, hot and cold rolled coils, electrogalvanized coils, electrical steel coils, hot-dip galvanized coils, and Ti/Ni-base alloy. The domestic market takes roughly 65% of CSC's production and the exports take the remaining 35%. CSC is the largest steel company in Taiwan, enjoying more than 50% of the domestic market. Major export destinations are Mainland China, Japan and Southeast Asia.

CSC is very active in innovation, and has strong capability to put the innovations into practice. The company's vision is: "We aspire to be a trustworthy steel company of global distinction that pursues growth, environmental protection, energy saving and value-innovation". CSC actively puts into practice its corporate values of "teamwork, entrepreneurial approach, down-to-earthiness and pursuit of innovation", as well as its operations beliefs of "promotion of social well-being, result orientation, implementation of teamwork, and emphasis on employees' self-realization." CSC keeps deepening the roots for its core business in steel, and devoted to integrate the related downstream industries to foster healthy development and international competitiveness of Taiwan's steel related industry.



Plant Greening



China Steel Corporation (CSC) is an integrated steel producer. After the completion of its phase II expansion construction on June 30, 1982, CSC launched its production of Hot Strip Mill. Products include hot rolled sheets, plates, coils, pickled and oiled coils, pickled and annealed coils, pickled and spheroidized coils. These products not only have huge production but they also come in a variety with a wide range of selection.

Through developments and improvements over the years, CSC's comprehensive steel products have fulfilled industrial requirements demanded by industries including structural steel uses like middle-high strength, buildings, welding, automobiles, and other various steel uses like forming, machine structure, high pressure vessel, superior atmospheric corrosion resistance steels, steel pipes, oil-gas flow line pipes..., etc. Moreover, in order to meet market demands, CSC has continually developed a series of CSC specification products, such as CSC ACR-TEN (atmospheric corrosion resistance steels), CSC 50BV30 (Cr-B-V alloy steels), CSC HC1085 (high carbon tool steels with thermo-stable coating), and CSC HC 15B22 (high strength manganese boron steels), etc.

CSC's hot rolled products have been approved by many certifications such as ISO 9001, JIS Mark, ISO/ TS16949 and IECQ QC080000 (Hazardous Substance Process Management). The approvals and qualifications are testament to CSC's commitment to reliable and superior products, thus providing its clients a peace of mind.

The vision of CSC's customer services is to gain customers' appreciation and trust and help them be successful, and the aim of that is to promote customers' technology and upgrade the steel industry.

In order to enhance the customer services, CSC adopts multi-step and multi-level service pattern which is characterized by emphasizing on (1) the pre-sale services for helping customers to choose suitable materials and improve their production processes; (2) handling complains and claims from customers with proper and rapid manner, and conducting customers the corresponding improvements to the root-causes; (3) providing customers with the developed high-grade materials to meet the upgrade policy for domestic industries.

The stable and reliable quality of CSC's steel products have gained the acceptance of domestic industries widely, and CSC has also been selected as the first priority provider to purchase their needed steel materials owing to CSC's quick and efficient technical services. CSC will continue to improve customer services and the technical technologies both for customers and CSC itself to promote steel-use industries' international competitiveness.



# 3

## **JFS A1001 JSH780R**

This grade of hot-rolled steel possesses high strength, excellent toughness and weldability and are applicable to high strength, thinning, light forming that are best used in automobile parts such as electric window lift mechanisms, door control rod, airbag components, and collision-resistant beams, etc.

## **CSC HM-690T**

This grade of hot-rolled steel possesses high strength, excellent toughness and weldability that are best used in general structural parts, light drawing processing, heavy duty machinery, and automobile parts.

## **JFS A1001 JSH590Y**

This grade of hot-rolled steel possesses high strength, excellent stretchability and are applicable to high strength, thinning, hard-to-form, ED coating, and electroplating.

## **CSC HC 15B22**

This grade of high strength boron-manganese hot-rolled steel possesses excellent formability and weldability and may attain strength of 1470MPa through subsequent quench and temper that are best used in automobile parts for improvement of crashworthiness.

## **API 5L X52M/X65M/X70M PSL2**

This grade of hot-rolled steel is applicable to API 5L X52M/X65M/X70M PSL2 welded oil line pipes, among which the X52M is supposed to use in harsh environments, may choose the specification with feature of resistance to hydrogen induced cracking (HIC) .

## **API 5CT J55U**

This grade of hot-rolled steel with low S. P. elements may improve toughness and weldability and is applicable to API 5CT J55 oil well casing. In addition, it can also promote customer to use API 5CT N80Q high-strength grade for increasing operation performance through customer's proper heat treatment.

---

## **EN10025-2 S355J0**

---

This grade of hot-rolled steel with low carbon equivalent and strength of 50 kgf possesses excellent low temperature toughness and weldability that are best used in steel pipe pile for bridge, underwater tunnel, coastal wall, breakwaters. The maximum ordering thickness is 25mm.

---

## **ASTM A572 GR.50 TYPE1**

---

This grade of high strength low-alloy hot-rolled steel is applicable to structural use that is best used in sections and stiffening plates.

---

## **CSC HC 1085**

---

This grade of high carbon hot-rolled steel refers JIS G4401 SK85 to specify and strengthens the feature of withstanding high temperature coating that is best used in gardening tools, hand tools, etc.

---

## **PA Steels (Pickled and Annealed coils)**

---

HR PA steel coils high-medium carbon, low alloy, tool steel grade as basis and through lowering their hardness and variance of mechanical properties will promote formability and mold life, applicable to tube making, blanking,bending, that are best used in cold-drawn bicycle tube, hydraulic tube, washers, knives, cold re-rolling.

---

## **PAS Steels (Pickled and Spheroidized coils)**

---

HR PAS steel coils have PA excellent features and additional spheroidized carbides that make medium-high carbon steel, low alloy, tool steel grade suitable for fine blanking, shaving, finish blanking, cold forging, hole expansion, drawing. Their typical uses include tooth plates, sliders, starter gears, bearing rings, sewing machine needle plates, etc.

# 4

## CERTIFICATION



ISO 9001 Certificate



IECQ Certificate



ISO/TS 16949 Certificate




JIS Mark 07007 Certificate



JIS MARK 07008 Certificate

# 5

## MANUFACTURING PROCESS AND MAJOR EQUIPMENTS



### MANUFACTURING FACILITIES

**Reheating Furnace**



Reheating furnaces are used to heat slabs to pre-defined temperature for hot rolling according to different heating curves based on steel grades.

**Roughing Mill**



Roughing mill is the main equipment to rolling both slab thickness and width to pre-calculated value for finishing rolling.

**Finishing Mill**



Tandem finishing mill further reduce strip thickness to customer ordered specification. The finishing temperature, strip profile, flatness and surface quality are also controlled to meet customers' requirements.

**Laminar Flow**



After finishing mill, the strip is cooled to proper temperature by laminar flow for achieving required mechanical and metallurgical properties.



**Down Coiler**



Hot strip is coiled by down coiler, then being packed, marked and delivered for customer or down stream plants.

## Production Facilities

Equipment Item	No. 1 HSM	No.2 HSM	No.3 HSM (Dragon Steel)
Reheating Furnace	4 Walking Beam Type Capacity: 250 ton/hr x 4	2 Walking Beam Type Capacity: 375 ton/hr x 2	2 Walking Beam Type Capacity: 300 ton/hr x 3
Slab Sizing Press	Flying Type	—	—
Vertical Edger	Caliber Type x4	Groove Type x1, Caliber Type x 1	Groove Type x1, Caliber Type x 1
Rougher R1	Two High	Two High	Two High
Rougher R2	Four High Reversing	Four High Reversing	Four High Reversing
Rougher R3	Four High	—	—
Rougher R4	Four High	—	—
Edge Heater	Elec-Magnet Induction	Elec-Magnet Induction	Elec-Magnet Induction
Finishing Mill	Four High Tandem (F1~F7) HAGC: F4~F7 WRS: F4~F7 ( ±150mm) WRB: F1~F7 (200t/Chock)	Four High Tandem (F1~F7) HAGC: F1~F7 WRS: F1~F7 ( ±200mm) WRB: F1~F7(200t/Chock)	Four High Tandem (F1~F7) HAGC: F1~F7, Pair Cross: F1~F4 WRS: F5~F7 ( ±200mm) WRB: F1~F4(120t/Chock) F5~F7(200t/Chock)
Down Coiler	Hydraulic Type x 3 Automatic Jumping Control	Hydraulic Type x 2 Automatic Jumping Control	Hydraulic Type x 2 Automatic Jumping Control

HAGC: Hydraulic Automatic Gauge Control	RAWC: Roughing mill Automatic Width Control
	
HAGC system is attached to finishing mill to control roll gap with hydraulic cylinders to achieve ordered thickness value.	RAWC system is attached to roughing mill vertical edgers to control strip width to ordered value.
WRS: Work Roll Shifting System	WRB: Work Roll Bending System
	
WRS system is to shift work roll horizontally to control the even wearing of roll surface and thus to control strip thickness distribution in width direction.	WRB system is to bend work roll with hydraulic cylinders to control strip crown to target value.

# 6

## APPLICATION EXAMPLES



## 7.1 Chemical Composition and Mechanical Requirements

### 7.1.1 CSC ACR-TEN Superior Atmospheric Corrosion Resistance Steel

Grade	Applicable thickness range (mm)	Chemical Composition %					Tension Test				Bendability		
		C	Si	Mn	P	S	Yield Strength N/mm <sup>2</sup>	Tensile Strength N/mm <sup>2</sup>	Elongation		Angle of bending	Inside Diameter	Test Piece
										Test Piece	%		
ACR-TEN A	1.6 ≤ 12.7	0.12 max.	0.25 ≤ 0.55	0.20 ≤ 0.50	0.070 ≤ 0.150	0.025 max.	345 min.	480 min.	No.5 in Rolling direction	25 min.	180°	thickness × 1.0	No.1 in Rolling direction
ACR-TEN AF	1.5 ≤ 12.7	0.08 max.	0.15 ≤ 0.45	0.15 ≤ 0.45			285 min.	410 ≤ 510					

Remark : 1. The values specified shall not apply to the irregular portions at both ends of steel strip.

2. To improve the atmospheric corrosion resistant steel material properties, adding appropriate amount of Cu, Cr, Ni and other alloying elements.

### 7.1.2 CSC Cr-B-V Alloy steel

Grade	Applicable thickness range (mm)	Chemical Composition %						
		C	Mn	P	S	Cr	B	V
CSC 50BV30	2.20~5.00	0.27~0.33	0.70~1.00	0.025 max.	0.015 max.	0.30 min.	0.0005 min.	0.10 min.

### 7.1.3 CSC HM-690T (high strength steel)

Grade	Applicable thickness range (mm)	Chemical Composition %					Tension Test				Bendability			
		C	Mn	P	S	Si	Yield Strength N/mm <sup>2</sup>	Tensile Strength N/mm <sup>2</sup>	Elongation % (transverse to rolling direction)		No.5 (Test Piece)	Inside Diameter	Test Piece	
										thickness (t) mm	thickness (t) mm			
CSC HM-690T	2.0~10.0	0.18 max.	1.60 max.	0.03 max.	0.015 max.	0.55 max.	550 min.	690 min.	2.0 ≤ t < 2.3	2.3 ≤ t < 6.3	6.3 ≤ t ≤ 10	180°	3.0t	4.0t
									t ≤ 6.0	6.0 ≤ t				

No.3  
Transverse  
to rolling  
direction

### 7.1.4 CSC HC 1085 (hot-rolled high carbon tool steel with thermostable coating)

Grade	Applicable thickness range (mm)	Chemical Composition %					
		C	Mn	P	S	Si	
CSC HC 1085	3.2~5.0	0.80~0.90	0.10~0.50	0.020max.	0.030max.	0.08max.	

Remark : Supply hot-rolled pickled and annealed (spheroidized) coil, and chemical composition guaranteed only.

### 7.1.5 CSC HC 15B22 (hot-rolled high-strength B-Mn steel)

Grade	Applicable thickness range (mm)	Chemical Composition %							
		C	Mn	P	S	Si	Al	B	
CSC HC 15B22	1.8~2.8	0.19~0.25	1.05~1.35	0.020max.	0.010max.	0.15~0.25	0.075max.	0.0005 ~ 0.0030	

Remark : Chemical composition guaranteed only.

### 7.1.6 JIS G3101 Rolled Steel for General Structure

Grade	Applicable thickness range (mm)	Chemical Composition %				Tension Test				Bendability		
		C	Mn	P	S	Yield Point or Yield Strength N/mm <sup>2</sup>	Tensile Strength N/mm <sup>2</sup>	Elongation %		Angle of bending	Inside radius	Test Piece
								No.5 Test Piece	No.1A Test Piece			
								thickness (t) mm	thickness (t) mm			
								t ≤ 5	5 < t ≤ 16			
SS330	16 max.					205min.	330 ~ 430	26min.	21min.	180°	0.5t	No.1
SS400	16 max.				0.050 max.	245min.	400 ~ 510	21min.	17min.		1.5t	
SS490	16 max.					285min.	490 ~ 610	19min.	15min.		2.0t	
SS540	16 max.	0.30 max.	1.60 max.	0.040 max.	0.040 max.	400min.	540 min.	16min.	13min.		2.0t	

Remark : 1. Alloy elements other than those shown in the above table may be added necessary.

2. The bend test may be omitted\*. However, when the purchaser designates, the test shall be performed.

\* It means that the test may be omitted by the manufacturer's decision, but it means that the bendability shall satisfy the specification.

### 7.1.7 JIS G3106 Rolled Steel for Welded Structure

Grade	Applicable thickness range (mm)	Chemical Composition %					Yield Point or Proof Strength N/mm <sup>2</sup>	Tensile Strength N/mm <sup>2</sup>	Tension Test			Impact Test			
		C	Si	Mn	P	S			Elongation %		Test Temperature °C	Charpy Absorbed Energy J	Test Piece		
									No.5 Test Piece	No.1A Test Piece					
									Thickness (t)mm	Thickness (t)mm					
							t ≤ 5	t ≤ 16	5 < t ≤ 16						
SM400A	16 max.	0.23 max.	—	2.5 × C min.	0.035 max.	0.035 max.	245 min.	400 ~ 510	23 min.	—	18 min.	—	—	No.4 in rolling direction	
SM400B	16 max.	0.20 max.	0.35 max.	0.60 ~ 1.50	0.035 max.	0.035 max.	245 min.	400 ~ 510	23 min.	—	18 min.	0	27 min.		
SM490A	16 max.	0.20 max.	0.55 max.	1.65	0.035 max.	0.035 max.	325 min.	490 ~ 610	22 min.	—	17 min.	—	—		
SM490B	16 max.	0.18 max.	0.55 max.	1.65	0.035 max.	0.035 max.	325 min.	490 ~ 610	22 min.	—	17 min.	0	27 min.		
SM490C	16 max.	0.18 max.	0.55 max.	1.65	0.035 max.	0.035 max.	325 min.	490 ~ 610	22 min.	—	17 min.	0	47 min.		
SM490YA	16 max.	0.20 max.	0.55 max.	1.65	0.035 max.	0.035 max.	365 min.	490 ~ 610	19 min.	—	15 min.	—	—		
SM520C	16 max.	0.20 max.	0.55 max.	1.65	0.035 max.	0.035 max.	365 min.	520 ~ 640	19 min.	—	15 min.	0	47 min.		
SM570	16 max.	0.18 max.	0.55 max.	1.70	0.035 max.	0.035 max.	460 min.	570 ~ 720	—	19 min.	—	-5	47 min.		

Remark : 1. Alloy elements other than those shown in the above table may be added necessary.

2. Impact test is applicable to thickness over 12.0mm of steel.

### 7.1.8 JIS G3113 Hot-Rolled Steel Plates, Sheets and Strip for Automobile Structural Uses

Grade	Applicable thickness range (mm)	Chemical Composition %		Tension Test										Bendability						
		P	S	Tensile Strength N/mm <sup>2</sup>	Yield Point N/mm <sup>2</sup>			Elongation % (rolling direction)						Angle of bending	Inside radius	Test piece				
					No.5 Test Piece						Thickness (t) mm									
					Thickness (t) mm		Thickness (t) mm						Thickness (t) mm							
					t < 6.0	6.0 ≤ t < 8.0	8.0 ≤ t < 14	1.6 ≤ t < 2.0	2.0 ≤ t < 2.5	2.5 ≤ t < 3.15	3.15 ≤ t < 4.0	4.0 ≤ t < 6.3	6.3 ≤ t < 14							
SAPH 310	1.6~14.0	0.040 max.	0.040 max.	310 min.	(185) min.	(185) min.	(175) min.	33 min.	34 min.	36 min.	38 min.	40 min.	41 min.	180°	Flat on itself	1.0t	No.3 transverse to rolling direction			
SAPH 370	1.6~14.0			370 min.	225 min.	225 min.	215 min.	32 min.	33 min.	35 min.	36 min.	37 min.	38 min.		0.5t	1.0t				
SAPH 400	1.6~14.0			400 min.	255 min.	235 min.	235 min.	31 min.	32 min.	34 min.	35 min.	36 min.	37 min.		1.0t	1.0t				
SAPH 440	1.6~14.0			440 min.	305 min.	295 min.	275 min.	29 min.	30 min.	32 min.	33 min.	34 min.	35 min.		1.0t	1.0t				

Remark : 1.Values in parentheses mean reference values.

2.The values specified shall not apply to the irregular portions at both ends of steel strip.

### 7.1.9 JIS G3116 Steel Sheets, Plate and Strip for Gas Cylinders

Grade	Applicable thickness range (mm)	Chemical Composition %					Tension Test				Bendability		
		C	Si	Mn	P	S	Yield Point or Proof Stress N/mm <sup>2</sup>	Tensile Strength N/mm <sup>2</sup>	Elongation %	Test Piece	Angle of bending	Inside radius	Thickness (t) mm
SG255	1.6~6.0	0.20 max.	—	0.30 min.	0.020 max.	0.020 max.	255 min.	400	28 min.	No.5 in rolling direction	180°	1.0t	No.3 in rolling direction
SG295	1.6~6.0	0.20 max.	0.35 max.	1.00 max.	0.020 max.	0.020 max.	295 min.	440	26 min.			1.5t	

Remark : The values specified shall not apply to the irregular portions at both ends of steel strip.

### 7.1.10 JIS G3125 Superior Atmospheric Corrosion Resisting Rolled Steels

Grade	Applicable thickness range (mm)	Chemical Composition %								Tension Test				Bendability		
		C	Si	Mn	P	S	Cu	Cr	Ni	Yield Point or Proof Stress N/mm <sup>2</sup>	Tensile Strength N/mm <sup>2</sup>	Elongation %	Test Piece	Angle of bending	Inside radius	Thickness (t) mm
SPA-H	t ≤ 6.0	0.12 max.	0.20 ~ 0.75	0.60 max.	0.070 ~ 0.150	0.035 max.	0.25 ~ 0.55	0.30 ~ 1.25	0.65 max.	355 min.	490 min.	No.5	22 min.	180°	0.5t	No.1 in rolling direction
	6.0 < t ≤ 16.0												15 min.		1.5t	

Remark : Alloy elements other than those shown in the above table may be added necessary.

### 7.1.11 JIS G3131 Hot-Rolled Mild Steel Plate, Sheets and Strip

Grade	Applicable thickness range (mm)	Chemical Composition %				Tensile Strength N/mm <sup>2</sup>	Tension Test						Bendability				
		C	Mn	P	S		Elongation % (Rolling direction)						Test Piece	Angle of bending	Inside radius	Test Piece	
							Thickness (t) mm								t < 3.2	3.2 ≤ t	
SPHC	1.2~14.0	0.12 max.	0.60 max.	0.045 max.	0.035 max.	270 min.	27 min.	29 min.	29 min.	29 min.	31 min.	31 min.	No.5 in rolling direction	180°	Flat on itself	0.5t	No.3 in rolling direction
SPHD	1.2~14.0	0.10 max.	0.45 max.	0.035 max.	0.035 max.		30 min.	32 min.	33 min.	35 min.	37 min.	39 min.		—	—	—	
SPHE	1.2~8.0	0.08 max.	0.40 max.	0.030 max.	0.030 max.		32 min.	34 min.	35 min.	37 min.	39 min.	41 min.		—	—	—	
SPHF	1.4~8.0	0.08 max.	0.35 max.	0.025 max.	0.025 max.		37 min.	38 min.	39 min.	39 min.	40 min.	42 min.		—	—	—	

Remark : 1. Grade SPHF is manufactured by a special process, such as made of killed steel to improve drawability.

2. The values specified shall not apply to the irregular portions at both ends of steel strip.

3. The bend test may be omitted\*. However, when the purchaser designates, the test shall be performed.

\* It means that the test may be omitted by the manufacturer's decision, but it means that the bendability shall satisfy the specification.

### 7.1.12 JIS G3132 Hot-Rolled Carbon Steel Strip for Pipes and Tubes

Grade	Applicable thickness range (mm)	Chemical Composition %					Tensile Strength N/mm <sup>2</sup>	Tension Test					Bendability			
		C	Si	Mn	P	S		Elongation %				Test piece	Angle of bending	Inside radius	Test Piece	
								Thickness (t) mm						t < 3.0	3.0 < t ≤ 13.0	
SPHT1	1.2~13.0	0.10 max.	0.35 max.	0.50 max.	0.040 max.	0.040 max.	270 min.	30 min.	32 min.	35 min.	37 min.	No.5 in rolling direction	180°	Flat on itself	0.5t	No.3 in rolling direction
SPHT2	1.2~13.0	0.18 max.	0.35 max.	0.60 max.				25 min.	27 min.	30 min.	32 min.			1.0t	1.5t	
SPHT3	1.6~13.0	0.25 max.		0.30 ~ 0.90				(20 min.)	22 min.	25 min.	27 min.			1.5t	2.0t	
SPHT4	1.6~13.0	0.30 max.		0.30 ~ 1.00				(15 min.)	18 min.	20 min.	22 min.			1.5t	2.0t	

Remark : 1. The Si content of SPHT1 can be modified to 0.04% max. upon agreement between the purchaser and manufacturer.

2. Values in parentheses mean reference values.

3. The values specified shall not apply to the irregular portions at both ends of steel strip.

4. The bend test may be omitted\*. However, when the purchaser designates, the test shall be performed.

\* It means that the test may be omitted by the manufacturer's decision, but it means that the bendability shall satisfy the specification.

### 7.1.13 JIS G3134 Hot-Rolled High Strength Steel Sheets with Improved Formability for Automobile Structural Uses

Grade	Applicable thickness range (mm)	Tensile Strength N/mm <sup>2</sup>	Yield Point or Proof Stress N/mm <sup>2</sup>	Elongation %				Test Piece	Bendability				
				Thickness(t) mm					Angle of bending	Inside radius		Test Piece	
				1.6 ≤ t < 2.0	2.0 ≤ t < 2.5	2.5 ≤ t < 3.25	3.25 ≤ t ≤ 6.0			Thickness(t) mm	1.6 ≤ t < 3.25	3.25 ≤ t < 6.00	
SPFH 490	1.6~6.0	490 min.	325 min.	22	23	24	25	No.5 transverse to rolling direction	180°	0.5t	1.0t	No.3 transverse to rolling direction	
SPFH 540	1.6~6.0	540 min.	355 min.	21	22	23	24			1.0t	1.5t		
SPFH 590	1.6~6.0	590 min.	420 min.	19	20	21	22			1.5t	1.5t		
SPFH 590Y	2.0~4.0	590 min.	325 min.	—	22	23	24			1.5t	1.5t		

Remark : 1. The chemical composition shall be agreed upon by the purchaser and manufacturer, if necessary.

2. The bend test may be omitted\*.However, when the purchaser designates, the test shall be performed.

\* It means that the test may be omitted by the manufacturer's decision, but it means that the bendability shall satisfy the specification.

### 7.1.14 JIS G3136 Rolled Steels for Building Structure

Grade	Applicable thickness range (mm)	Chemical Composition %					Carbon Equivalent %	Yield Point or Proof Stress N/mm <sup>2</sup>	Tensile Strength N/mm <sup>2</sup>	Yield Ratio %		Elongation %	
		Thickness(t) mm								Test Piece No.1A		Thickness(t) mm	
		C	Si	Mn	P	S	t ≤ 20	6 ≤ t < 12	12 ≤ t ≤ 20	6 ≤ t < 12	12 ≤ t ≤ 16	6 ≤ t ≤ 16	16 < t ≤ 20
										400	—	—	17 min.
SN400A	6.0~20.0	0.24 max.	—	—	0.050 max.	0.050 max.	—	235 min.	235 min.	400 ~ 510	—	—	21 min.
SN400B	6.0~20.0	0.20 max.	0.35 max.	0.60 ~ 1.50	0.030 max.	0.015 max.	0.36 max.	235 min.	235 ~ 355		—	80 max.	18 min.
SN490B	6.0~20.0	0.18 max.	0.55 max.	1.65 max.			0.44 max.	325 min.	325 ~ 445	490 ~ 610	—	80 max.	17 min.

Remark : 1. Impact test for SN400B and SN490B is applicable to thickness over 12.0mm of steel. Test temperature at 0°C , charpy absorption energy is

27J min. , test piece is No.4 in rolling direction.

$$2.\text{Carbon Equivalent} = C + \frac{Mn}{6} + \frac{Si}{24} + \frac{Ni}{40} + \frac{Cr}{5} + \frac{Mo}{4} + \frac{V}{14}$$

### 7.1.15 SAE J403 Carbon Steel

Grade	Chemical Composition %				
	C	Si	Mn	P	S
1005 <sup>(1)</sup>	0.06max.		0.35max.		
1006 <sup>(1) (2)</sup>	0.08max.		0.25~0.40		
1008 <sup>(1) (2)</sup>	0.10max.		0.30~0.50		
1010	0.08~0.13		0.30~0.60		
1012	0.10~0.15		0.30~0.60		
1015	0.13~0.18		0.30~0.60		
1016	0.13~0.18		0.60~0.90		
1017	0.15~0.20		0.30~0.60		
1018	0.15~0.20		0.60~0.90		
1019	0.15~0.20		0.70~1.00		
1020	0.18~0.23		0.30~0.60		
1021	0.18~0.23		0.60~0.90		
1022	0.18~0.23		0.70~1.00		
1023	0.20~0.25		0.30~0.60		
1026	0.22~0.28		0.60~0.90		
1030	0.28~0.34		0.60~0.90		
1033	0.30~0.36		0.70~1.00		
1035	0.32~0.38		0.60~0.90		
1038	0.35~0.42		0.60~0.90		
1040	0.37~0.44		0.60~0.90		
1045	0.43~0.50		0.60~0.90		
1049	0.46~0.53		0.60~0.90		
1050	0.48~0.55		0.60~0.90		
1055	0.50~0.60		0.60~0.90		
1060	0.55~0.65		0.60~0.90		
1065	0.60~0.70		0.60~0.90		
1070	0.65~0.75		0.60~0.90		
1086	0.80~0.93		0.60~0.90		
1524	0.19~0.25	—	1.35~1.65	0.030max.	0.050max.
1536	0.30~0.37	—	1.20~1.50	0.030max.	0.050max.
1541	0.36~0.44	—	1.20~1.50	0.030max.	0.050max.
1552	0.47~0.55	—	1.35~1.65	0.030max.	0.050max.

Remark : 1.Ultra low carbon, interstitial free stabilized and nonstabilized steel may be supplied for these grades .

2. MANGANESE—For grades G10060 and G10080 applicable to Structural Shapes, Plates, Strip, Sheets and Welded Tubing, the manganese limit is 0.45% maximum and 0.50% maximum, respectively, with no minimum.

### 7.1.16 SAE J404 Alloy Steel

Grade	Chemical Composition %							
	C	Si	Mn	P	S	Ni	Cr	Mo
4130	0.28~0.33	0.15~0.35	0.40~0.60	0.030max.	0.040max.	—	0.80~1.10	0.15~0.25

Remark : The Si content can be modified upon agreement between the purchaser and manufacturer.

### 7.1.17 JIS G4051 Carbon Steels for Machine Structural Use

Grade	Chemical Composition %				
	C	Si	Mn	P	S
S10C	0.08~0.13	0.15~0.35	0.30~0.60	0.030max.	0.035max.
S17C	0.15~0.20		0.30~0.60		
S35C	0.32~0.38		0.60~0.90		
S40C	0.37~0.43		0.60~0.90		
S45C	0.42~0.48		0.60~0.90		
S50C	0.47~0.53		0.60~0.90		
S53C	0.50~0.56		0.60~0.90		
S55C	0.52~0.58		0.60~0.90		

### 7.1.18 JIS G4053 Cr-Mo Steel

Grade	Chemical Composition %							
	C	Si	Mn	P	S	Ni	Cr	Mo
SCM415	0.13~0.18	0.15~0.35	0.60~0.90	0.030max.	0.030max.	0.25max.	0.90~1.20	0.15~0.25
SCM420	0.18~0.23							
SCM435	0.33~0.38							
SCM440	0.38~0.43							0.15~0.30

Remark : As impurities, Cu shall not exceed 0.30% throughout all grades.

### 7.1.19 SAE J1392 High Strength Steel

Grade	Chemical Composition %		Tension Test				Bendability			
			Yield Strength N/mm <sup>2</sup>	Tensile Strength N/mm <sup>2</sup>	Elongation %	Test Piece	Angle of bending	Inside Radius		Test Piece
	C	Mn						Thickness(t) mm	t ≤ 4.55	
050XLF	0.13 max.	0.90 max.	340min.	410min.	22min.	In rolling direction	90°	1.0t	2.0t	Transverse to rolling direction
060XLF			410min.	480min.	20min.					
080XLF	0.13 max.	1.65 max.	550min.	620min.	14min.					

### 7.1.20 ASTM A36, A283 Carbon Steel for Structural Use

ASTM No (Description)	Applicable thickness range in. (mm)	Chemical Composition %					Tension Test			
		C	Si	Mn	P	S	Yield Point ksi (N/mm <sup>2</sup> )	Tensile Strength ksi (N/mm <sup>2</sup> )	Elongation	
A36 (Structural Quality)	t ≤ 3/4 (19.05)	0.25 max.	0.40 max.	—	0.040 max.	0.050 max.	36(250) min.	58~80 (400~550)	8(200)	20
	3/4 (19.05) < t ≤ 3/2 (38.1)	0.25 max.	0.40 max.	0.8 <sub>z</sub> 1.2	0.040 max.	0.050 max.	36(250) min.	58~80 (400~550)	2 (50)	23
A283 Grade C (Low and Intermediate Tensile Strength)	—	0.24 max.	0.40 max.	0.90 max.	0.035 max.	0.040 max.	30(205) min.	55~75 (380~515)	8(200)	22
									2 (50)	25

Remark : 1.Cu is 0.20% min. when specified.

2. "t" is the thickness of material.

**7.1.21 ASTM A1011 Carbon, structural, High-Strength Low-Alloy Steel and High-Strength Low-Alloy with Improved Formability. <thickness less than 0.23 in. (6mm)>**

Grade	Chemical Composition %											
	C	Mn	P	S	Al	Cu	Ni	Cr	Mo	V	Nb	Ti
CS Type B	0.02~0.15	0.60 max.	0.030 max.	0.035 max.	—							
DS Type B	0.02~0.08	0.50 max.	0.020 max.	0.030 max.	0.01 min.				0.06 max.	0.008 max.	0.008 max.	0.025 <sup>(1)</sup> max.
SS Gr. 36 Type 2	0.25 max.	1.35 max.	0.035 max.	0.040 max.	—	0.20 max.	0.20	0.15 max. <sup>(1)</sup>				
HSLAS Gr.45 Class 1	0.22 max.	1.35 max.	0.040 max.						0.06 max.			
HSLAS-F Gr.50	0.15 max.			0.025 max.	—				0.16 max.	0.005 min.	0.005 min.	0.005 min.
HSLAS-F Gr.60		1.65 max.	0.020 max.									
HSLAS-F Gr.70									0.16 max.			
HSLAS-F Gr.80												

Remark : 1. Cr is 0.25% maximum when C  $\leq$  0.05%. Ti is permitted for SS designations to the lesser of (3.4N+1.5S) or 0.025% maximum, when C  $\geq$  0.02%,.

2. Nb, Ti and V is 0.005% min. when specified.

Grade	Tensile Strength MPa	Yield Strength Mpa	Elongation % G.L.=2 inch				Bend Test (Inside Radius)	
		Thickness (t) mm	Thickness (t) mm			Test Piece	Thickness (t) mm	Test Piece
		t<6.0	t<1.6	1.6 $\leq$ t <2.5	t=2.5		t<6.0	
CS Type B	—	205~340	25min.	25min.	25min.	25min.	—	
DS Type B	—	205~310	28min.	28min.	28min.	28min.	—	
SS Gr. 36 Type2	400~550	250min.	16min.	20min.	21min.	21min.	2.0t	
HSLAS Gr.45 Class 1	410min.	310min.	23min.	23min.	23min.	25min.	1.5t	
HSLAS-F Gr.50	410min.	340min.	22min.	22min.	22min.	24min.	1.0t	
HSLAS-F Gr.60	480min.	410min.	20min.	20min.	20min.	22min.	1.5t	
HSLAS-F Gr.70	550min.	480min.	18min.	18min.	18min.	20min.	2.0t	
HSLAS-F Gr.80	620min.	550min.	16min.	16min.	16min.	18min.	2.0t	

### 7.1.22 ASTM A1018 Heavy-thickness for Carbon, Commercial, drawing, structural steel, High-Strength

#### Low-Alloy, and High-Strength Low-Alloy Steel with Improved Formability

Grade	Chemical Composition %											
	C	Mn	P	S	Cu	Ni	Cr	Mo	V	Nb	Ti	N
HSLAS-F Gr.80	0.15 max.	1.65 max.	0.025 max.	0.035 max.	0.20 max.	0.20 max.	0.15 max.	0.16 max.	0.005 min.	0.005 min.	0.005 min.	—

Remark : 1. Cu + Ni + Cr + Mo  $\leq 0.50$

2. Nb, Ti and V is 0.005% min. when specified.

Grade	Tensile Strength MPa	Yield Strength Mpa	Elongation %			Bend Test (Inside Radius)	
		Thickness (t) mm	Thickness (t) mm			Thickness (t) mm	
		6 $\leq$ t $\leq$ 25	G.L.= 2 inch t $\leq$ 25	G.L.= 8 inch t $\leq$ 25	Test Piece	t $\leq$ 25	Test Piece
HSLAS-F Gr.80	620min.	550min.	12min.	10min.	Transverse to rolling direction	2.0t	Transverse to rolling direction

### 7.1.23 ASTM A572 GR.50 TYPE1 High-Strength Low-Alloy Steel

Grade	Chemical Composition %						Tension Test		
	C	Mn	P	S	Si	Nb	Yield Strength N/mm <sup>2</sup>	Tensile Strength N/mm <sup>2</sup>	Elongation %
ASTM A572 GR.50 TYPE1	0.23 max.	1.35 max.	0.040 max.	0.050 max.	0.40 max.	0.005 ± 0.050	345min.	450min.	18min.

### 7.1.24 EN10111 Continuously Hot Rolled Low Carbon Steel Sheet and Strip for Cold Forming

Grade	Steel No.	Applicable thickness range (mm)	Chemical Composition%				Tension Test (transverse to rolling direction)									
			C	Mn	P	S	Yield Strength N/mm <sup>2</sup>	Tensile Strength N/mm <sup>2</sup>	Elongation %			G.L.= 5.65 $\sqrt{S_0}$	Thickness (t)mm			
									Thickness (t)mm							
							1.0 $\leq$ t < 2.0	2.0 $\leq$ t $\leq$ 11.0	1.0 $\leq$ t < 1.5	1.5 $\leq$ t < 2	2 $\leq$ t < 3		3 $\leq$ t $\leq$ 11			
DD11	1.0332	1.0~11.0	0.12 max.	0.60 max.	0.045 max.	0.045 max.	170~360	170~340	440 max.	22min.	23min.	24min.	28min.			
DD12	1.0398	1.0~11.0	0.10 max.	0.45 max.	0.035 max.	0.035 max.	170~340	170~320	420 max.	24min.	25min.	26min.	30min.			
DD13	1.0335	1.0~11.0	0.08 max.	0.40 max.	0.030 max.	0.030 max.	170~330	170~310	400 max.	27min.	28min.	29min.	33min.			

Remark : "S<sub>0</sub>" : Test piece section area.

## 7.1.25 EN 10149-2 Hot-Rolled Flat Products Made of High Yield Strength Steels for Cold Forming

Grade	Steel No.	Chemical Composition %										
		C	Mn	Si	P	S <sup>(2)</sup>	Al total	Nb <sup>(1)</sup>	V <sup>(1)</sup>	Ti <sup>(1)</sup>	Mo	B
S315MC	1.0972	0.12 max.	1.30 max.	0.50 max.	0.020 max.	0.25 max.	0.015 min.	0.09 max.	0.20 max.	0.15 max.	—	—
S355MC	1.0976		1.50 max.	0.50 max.								
S420MC	1.0980		1.60 max.	0.50 max.								
S460MC	1.0982		1.60 max.	0.50 max.								
S500MC	1.0984		1.70 max.	0.50 max.								
S550MC	1.0986		1.80 max.	0.50 max.								
S600MC	1.8969		1.90 max.	0.50 max.								
S650MC	1.8976		2.00 max.	0.60 max.								
S700MC	1.8974		2.10 max.	—								

Remark : 1. Nb + V + Ti ≤ 0.22

2. The S content can be modified to 0.010% max. upon agreement between the purchaser and the manufacturer.

Grade	Steel No.	Yield Strength N/mm <sup>2</sup>	Tensile Strength N/mm <sup>2</sup>	Elongation% (in rolling direction)		Bend Test (Inside Diameter)	
				thickness(t) mm			
				t < 3 G.L.=80mm	3 ≤ t G.L.=5.65√S <sub>0</sub>		
S315MC	1.0972	315min.	390~510	20min.	24min.	Flat on itself	
S355MC	1.0976	355min.	430~550	19min.	23min.	0.5t	
S420MC	1.0980	420min.	480~620	16min.	19min.	0.5t	
S460MC	1.0982	460min.	520~670	14min.	17min.	1.0t	
S500MC	1.0984	500min.	550~700	12min.	14min.	1.0t	
S550MC	1.0986	550min.	600~760	12min.	14min.	1.5t	
S600MC	1.8969	600min.	650~820	11min.	13min.	1.5t	
S650MC	1.8976	650min.	700~880	10min.	12min.	2.0t	
S700MC	1.8974	700min.	750~950	10min.	12min.	2.0t	

Remark : 1. "S<sub>0</sub>" : Test piece section area.

2. t > 8mm : yield strength of S650MC and S700MC can be lower by 20 N/mm<sup>2</sup>.

## 7.1.26 EN 10025-2 Structural Steel

Grade	Steel No.	Chemical Composition %							
		C	Mn	Si	P	S	N	Cu	CEV
S235JR	1.0038	0.17 max.	1.40 max.	—	0.035 max.	0.035 max.	0.012 max.	0.55 max.	0.35 max.
S235J2	1.0117	0.17 max.	1.40 max.	—	0.025 max.	0.025 max.	—	0.55 max.	0.35 max.
S275JR	1.0044	0.21 max.	1.50 max.	—	0.035 max.	0.035 max.	0.012 max.	0.55 max.	0.40 max.
S355JR	1.0045	0.24 max.	1.60 max.	0.55 max.	0.035 max.	0.035 max.	0.012 max.	0.55 max.	0.45 max.
S355J0	1.0553	0.20 max.	1.60 max.	0.55 max.	0.030 max.	0.030 max.	0.012 max.	0.55 max.	0.45 max.
S355J2	1.0577	0.20 max.	1.60 max.	0.55 max.	0.025 max.	0.025 max.	—	0.55 max.	0.45 max.

Remark : 1. CEV=C +  $\frac{Mn}{6}$  +  $\frac{Si}{24}$  +  $\frac{Ni}{40}$  +  $\frac{Cr}{5}$  +  $\frac{Mo}{4}$  +  $\frac{V}{14}$

Grade	Steel No.	Tension Test (transverse to rolling direction)								Impact Test					
		Yield Strength N/mm <sup>2</sup>	Tensile Strength N/mm <sup>2</sup>	Elongation%						Test Temperature °C	Charpy Absorbed Energy J	Test Piece			
				G.L.=80mm			G.L.= $5.65\sqrt{S_o}$								
		Thickness(t) mm	Thickness(t) mm	Thickness(t) mm				Thickness(t) mm	In rolling direction						
		t ≤ 16 16 < t ≤ 25	t < 3	3 ≤ t ≤ 1.5	1 < t ≤ 2	1.5 < t ≤ 2	2 < t ≤ 2.5	2.5 < t < 3							
S235JR	1.0038	235 min.	225 min.	360~ 510	360~ 510	16 min.	17 min.	18 min.	19 min.	20	27 min.				
S235J2	1.0117	235 min.	225 min.	360~ 510	360~ 510	16 min.	17 min.	18 min.	19 min.	-20	27 min.				
S275JR	1.0044	275 min.	265 min.	430~ 580	310~ 560	14 min.	15 min.	16 min.	17 min.	20	27 min.				
S355JR	1.0045	355 min.	345 min.	510~ 680	470~ 630	13 min.	14 min.	15 min.	16 min.	20	27 min.				
S355J0	1.0553	355 min.	345 min.	360~ 510	470~ 630	13 min.	14 min.	15 min.	16 min.	0	27 min.				
S355J2	1.0577	355 min.	345 min.	360~ 510	470~ 630	13 min.	14 min.	15 min.	16 min.	-20	27 min.				

Remark : 1. "S<sub>o</sub>" : Test piece section area.

2. Impact test is applicable to thickness not less than 6.0mm of steel.

### 7.1.27 API 5L (Line Pipe)

Type of pipe	Level	Grade	Chemical Composition %					Tension Test				
			C max.	Mn max.	Si max.	P max.	S max.	Yield Strength psi (MPa)	Tensile Strength psi (MPa)			
Welded	PSL1	B	0.26	1.20	—	0.030	0.030	35500 (245) min.	60200 (415) min.			
		X42		1.30				42100 (290) min.	60200 (415) min.			
		X46		1.40				46400 (320) min.	63100 (435) min.			
		X52						52200 (360) min.	66700 (460) min.			
		X56						56600 (390) min.	71100 (490) min.			
		X60						60200 (415) min.	75400 (520) min.			
		X65		1.45				65300 (450) min.	77600 (535) min.			
	PSL2	BM	0.22	1.20	0.45	0.025	0.015	35500~65300 (245~450)	60200~110200 (415~760)			
		X42M		1.30				42100~71800 (290~495)	60200~110200 (415~760)			
		X46M		46400~76100 (320~525)				63100~110200 (435~760)				
		X52M		52200~76900 (360~530)				66700~110200 (460~760)				
		X56M		56600~79000 (390~545)				71100~110200 (490~760)				
		X60M		0.12	1.60			60200~81900 (415~565)	75400~110200 (520~760)			
		X65M						65300~87000 (450~600)	77600~110200 (535~760)			

Remark : 1. For each reduction of 0.01 % below the specified maximum for carbon, an increase of 0.05 % above the specified maximum for manganese is permissible, up to a maximum of 1.65 % for grades  $\geq$  L245 or B, but  $\leq$  L360 or X52; up to a maximum of 1.75 % for grades > L360 or X52, but < L485 or X70.

2. For Grade B –X65 and Grade X52M –X65M, the sum of the Nb, V, Ti contents shall not exceed 0.15%.

3. For Grade BM –X46M, Nb/ V/ Ti contents shall not exceed 0.05%/0.05%/0.04% separately.

4. The purchase order shall include type of pipe.

### 7.1.28 API 5CT (Casing and Tubing)

Grade	Chemical Composition (%)					Tension Test	
	C	Mn	P max.	S max.	Yield Strength MPa	Tensile Strength MPa	
J55	—	—	0.030	0.030	379~552	517min.	

Remark : The purchase order shall include type of pipe.

## 7.2 Tolerances

### 7.2.1 JIS G3113 Thickness Tolerances of Hot-Rolled Plates, Sheets and Coils

Unit : mm

Thickness(t) \ Width(w)	w < 1200	1200 ≤ w < 1500	1500 ≤ w < 1800	1800 ≤ w ≤ 1880
1.60 ≤ t < 2.00	±0.16	±0.17	±0.18	—
2.00 ≤ t < 2.50	±0.17	±0.19	±0.21	—
2.50 ≤ t < 3.15	±0.19	±0.21	±0.24	—
3.15 ≤ t < 4.00	±0.21	±0.23	±0.26	—
4.00 ≤ t < 5.00	±0.24	±0.26	±0.28	±0.29
5.00 ≤ t < 6.00	±0.26	±0.28	±0.29	±0.31
6.00 ≤ t < 8.00	±0.29	±0.30	±0.31	±0.35
8.00 ≤ t < 10.0	±0.32	±0.33	±0.34	±0.40
10.0 ≤ t < 12.5	±0.35	±0.36	±0.37	±0.45
12.5 ≤ t ≤ 14.0	±0.38	±0.39	±0.40	±0.50

Remark : 1. The positions where the thickness is to be measured shall be as follows:

(A) For mill-edged products, any point 25mm and over inward from the edge.

(B) For cut-edged products, any point 15mm and over inward from the edge.

2. The values specified shall not apply to the irregular portions at both ends of steel coils.

### 7.2.2 JIS G3116 Thickness Tolerances of Hot-Rolled Steel Plates, Sheets and Coils

Unit : mm

Thickness(t) \ Width(w)	600 ≤ w < 1200	1200 ≤ w < 1500	1500 ≤ w < 1800	1800 ≤ w ≤ 1880
1.60 ≤ t < 2.00	±0.16	±0.17	±0.18	±0.21
2.00 ≤ t < 2.50	±0.17	±0.19	±0.21	±0.25
2.50 ≤ t < 3.15	±0.19	±0.21	±0.24	±0.26
3.15 ≤ t < 4.00	±0.21	±0.23	±0.26	±0.27
4.00 ≤ t < 5.00	±0.24	±0.26	±0.28	±0.29
5.00 ≤ t < 6.00	±0.26	±0.28	±0.29	±0.31
t = 6.00	±0.29	±0.30	±0.31	±0.35

Remark : 1. The above table applies to SG255 and SG295.

2. Thickness shall be measured at any point of 20mm and over inside the edges.

3. The values specified shall not apply to the irregular portions at both ends of steel coils.

### 7.2.3 JIS G3131 Thickness Tolerances of Hot-Rolled Steel Plates, Sheets and Coils

Unit : mm

Thickness (t) \ Width(w)	w < 1200	1200 ≤ w < 1500	1500 ≤ w < 1800	1800 ≤ w ≤ 1880
t < 1.60	±0.14	±0.15	±0.16 <sup>(1)</sup>	—
1.60 ≤ t < 2.00	±0.16	±0.17	±0.18	±0.21
2.00 ≤ t < 2.50	±0.17	±0.19	±0.21	±0.25
2.50 ≤ t < 3.15	±0.19	±0.21	±0.24	±0.26
3.15 ≤ t < 4.00	±0.21	±0.23	±0.26	±0.27
4.00 ≤ t < 5.00	±0.24	±0.26	±0.28	±0.29
5.00 ≤ t < 6.00	±0.26	±0.28	±0.29	±0.31
6.00 ≤ t < 8.00	±0.29	±0.30	±0.31	±0.35
8.00 ≤ t < 10.0	±0.32	±0.33	±0.34	±0.40
10.0 ≤ t < 12.5	±0.35	±0.36	±0.37	±0.45
12.5 ≤ t ≤ 14.0	±0.38	±0.39	±0.40	±0.50

Remark : 1. The above table applies to SPHC, SPHD, SPHE and SPHF grades.

2. Thickness shall be measured at any point of 20mm and over inside the edges.

3. The values specified shall not apply to the irregular portions at both ends of steel coils.

Note 1. The value shall be applied to the steel strip under 1600mm in width.

### 7.2.4 JIS G3132 Thickness Tolerances of Hot-Rolled Steel Coils (SPHT1~ SPHT3)

Unit : mm

Thickness (t) \ Width(w)	w < 1200	1200 ≤ w < 1500	1500 ≤ w < 1800	1800 ≤ w ≤ 1880
t < 1.60	(±0.14) <sup>(2)</sup>	±0.15	±0.16 <sup>(1)</sup>	—
1.60 ≤ t < 2.00	±0.16	±0.17	±0.18	±0.21
2.00 ≤ t < 2.50	±0.17	±0.19	±0.21	±0.25
2.50 ≤ t < 3.15	±0.19	±0.21	±0.24	±0.26
3.15 ≤ t < 4.00	±0.21	±0.23	±0.26	±0.27
4.00 ≤ t < 5.00	±0.24	±0.26	±0.28	±0.29
5.00 ≤ t < 6.00	±0.26	±0.28	±0.29	±0.31
6.00 ≤ t < 8.00	±0.29	±0.30	±0.31	±0.35
8.00 ≤ t < 10.0	±0.32	±0.33	±0.34	±0.40
10.0 ≤ t < 12.5	±0.35	±0.36	±0.37	±0.45
12.5 ≤ t ≤ 13.0	±0.38	±0.39	±0.40	±0.50

Remark : 1. The above table applies to SPHT1~3 and CSC ACR-TEN grades.

2. Thickness shall be measured at any point 20mm and over inside the edges.

3. The values specified shall not apply to the irregular portions at both ends of steel coils.

Note 1. The value shall be applied to the steel strip under 1600mm in width.

2.Values in parentheses mean reference values.

### 7.2.5 JIS G3132 Thickness Tolerances of Hot-Rolled Steel Coils (SPHT4)

Unit : mm

Thickness (t) \ Width(w)	w < 1200	1200 ≤ w < 1500	1500 ≤ w < 1800	1800 ≤ w ≤ 1880
t < 1.60	(±0.14) <sup>(2)</sup>	±0.15	±0.16 <sup>(1)</sup>	—
1.60 ≤ t < 2.00	±0.16	±0.19	±0.20	—
2.00 ≤ t < 2.50	±0.18	±0.22	±0.23	±0.25
2.50 ≤ t < 3.15	±0.20	±0.24	±0.26	±0.29
3.15 ≤ t < 4.00	±0.23	±0.26	±0.28	±0.30
4.00 ≤ t < 5.00	±0.26	±0.29	±0.31	±0.32
5.00 ≤ t < 6.00	±0.29	±0.31	±0.32	±0.34
6.00 ≤ t < 8.00	±0.32	±0.33	±0.34	±0.38
8.00 ≤ t < 10.0	±0.35	±0.36	±0.37	±0.44
10.0 ≤ t < 12.5	±0.38	±0.40	±0.41	±0.49
12.5 ≤ t ≤ 13.0	±0.41	±0.44	±0.45	±0.54

Remark : 1. The above table applies to SPHT4 and CSC ACR-TEN grades.

2. Thickness shall be measured at any point 20mm and over inside the edges.

3. The values specified shall not apply to the irregular portions at both ends of steel coils.

Note 1. The value shall be applied to the steel strip under 1600mm in width.

2. Values in parentheses mean reference values.

### 7.2.6 JIS G3134 Thickness Tolerances of Hot-Rolled High Strength Steel Sheets with Improved for Formability

for Automobile Structural Uses

Unit : mm

Thickness (t) \ Width(w)	w < 1200	1200 ≤ w < 1500	1500 ≤ w < 1800	1800 ≤ w ≤ 1880
1.60 ≤ t < 2.00	±0.16	±0.19	±0.20 <sup>(1)</sup>	—
2.00 ≤ t < 2.50	±0.18	±0.22	±0.23 <sup>(1)</sup>	—
2.50 ≤ t < 3.15	±0.20	±0.24	±0.26 <sup>(1)</sup>	—
3.15 ≤ t < 4.00	±0.23	±0.26	±0.28	±0.30
4.00 ≤ t < 5.00	±0.26	±0.29	±0.31	±0.32
5.00 ≤ t < 6.00	±0.29	±0.31	±0.32	±0.34
t = 6.00	±0.32	±0.33	±0.34	±0.38

Remark : 1. The positions where the thickness is to be measured shall be as follows:

(A) For mill-edged products, any point 25mm and over inward from the edges.

(B) For cut-edged products, any point 15mm and over inward from the edges.

2. The values specified shall not apply to the irregular portions at both ends of steel coils.

Note 1. The values are applicable to the steel sheets and coils under 1600 mm in width.

### 7.2.7 JIS G3136 Thickness Tolerances of Rolled Steel for Building Structure

Unit : mm

Thickness (t)	Width(w)	w < 1600	1600 ≤ w ≤ 1880
6.00 ≤ t < 6.30		+0.70 -0.30	+0.90 -0.30
6.30 ≤ t < 10.0		+0.80 -0.30	+1.00 -0.30
10.0 ≤ t < 16.0		+0.80 -0.30	+1.00 -0.30

Remark : 1.The above table applies to SN400A,SN400B, and SN490B grades.

2. The positions where the thickness is to be measured shall be as follows:

- (A) For mill-edged products, any point 25mm and over inward from the edges.
- (B) For cut-edged products, any point 15mm and over inward from the edges.

### 7.2.8 JIS G3193 Thickness Tolerances of Hot-Rolled Steel Plates, Sheets and Coils

Unit : mm

Thickness (t)	Width(w)	w < 1600	1600 ≤ w ≤ 1880
t < 1.25		±0.16	—
1.25 ≤ t < 1.60		±0.18	—
1.60 ≤ t < 2.00		±0.19	±0.23
2.00 ≤ t < 2.50		±0.20	±0.25
2.50 ≤ t < 3.15		±0.22	±0.29
3.15 ≤ t < 4.00		±0.24	±0.34
4.00 ≤ t < 5.00		±0.45	±0.55
5.00 ≤ t < 6.30		±0.50	±0.60
6.30 ≤ t < 10.0		±0.55	±0.65
10.0 ≤ t < 16.0		±0.55	±0.65
16.0 ≤ t ≤ 20.0		±0.65	±0.75

Remark : 1. The above table applies to SS,SM,SCM,SPA-H, and SXXC grades.

2. The positions where the thickness is to be measured shall be as follows :

- (A) For mill-edged products, any point 25mm and over inward from the edges.
- (B) For cut-edged products, any point 15mm and over inward from the edges.

3. Tolerance given in the table may be limited to either plus side or minus side upon the agreement between the purchaser and the supplier.

The total tolerance range in this case shall be equal to that given in this table.

### 7.2.9 JIS G3193 Width Tolerances of Hot-Rolled Steel Plates, Sheets and Coils

Unit : mm

Width (w)	Thickness (t)	Tolerance			
		Mill edge		Cut edge ( by ordinary cutting )	
		max.	min.	max.	min.
630 ≤ w < 1000	1.20 ≤ t < 20.0	25	0	10	0
1000 ≤ w < 1250	t < 6.00	30	0	10	0
	6.00 ≤ t < 20.0			15	
1250 ≤ w < 1600	t < 6.00	35	0	10	0
	6.00 ≤ t < 20.0			15	
1600 ≤ w ≤ 1880	t < 6.00	40	0	10	0
	6.00 ≤ t < 20.0			20	

### 7.2.10 JIS G3193 Length Tolerances of Hot-Rolled Steel Plates and Sheets

Unit : mm

Length (L)	Tolerances	
	by ordinary cutting	
	max.	min.
L < 4000	20	0
4000 ≤ L < 6000	30	0
6000 ≤ L < 8000	40	0

### 7.2.11 JIS G3193 Camber Tolerances of Hot-Rolled Steel Strip, Plate and Sheet

#### 7.2.11.1 JIS G3193 Camber Tolerances of Hot-Rolled Steel Strip

Unit : mm

Width (w)	Maximum value
250 ≤ w	5 in any 2000 length

#### 7.2.11.2 JIS G3193 Camber Tolerances of Hot-Rolled Steel Plate and Sheet

The maximum value of camber of the steel plate and sheet shall be 0.2% or under of the length of the steel plate and sheet.

### 7.2.12 JIS G3193 Maximum Flatness of Hot-Rolled Steel Plates and Sheets

Unit : mm

Thickness (t)	Length for measurement <sup>(2)</sup>			
	2000			4000
	Width (w)			Width (w)
	w < 1250	1250 ≤ w < 1600	1600 ≤ w ≤ 1880	w < 2000
t < 1.60	18max.	20max.	—	—
1.60 ≤ t < 3.15	16max.	18max.	20max.	—
3.15 ≤ t < 4.00	16max.			—
4.00 ≤ t < 5.00	14max.			26max.
5.00 ≤ t < 8.00	13max.			22max.
8.00 ≤ t < 15.00	12max.			12max.

Remark : 1. The table is not applicable by the plate and sheet leveling done after leveling machine.

2. Values in this table shall be applied to any 2000 mm length. For the steel plate and sheet under 2000 mm in length, the values shall be applied to the full length. For the steel plate and sheet over 2000 mm in wave pitch, the values in this table shall be applied to any pitch of the wave. For those over 4000 mm in wave pitch, however, the above values shall be applied to any 4000 mm length.
3. Unless otherwise specified, 1.5 times the maximum deviation from flatness specified in this table shall be applied to the steel plate and sheet of which the lower limit of yield point or proof strength in tensile test is at least 460N/mm<sup>2</sup>, or chemical position on hardness is equivalent thereto, or quenched and tempered.
4. Measurement of flatness, as a rule, shall be made on a flat surface plate.
5. The table does not apply to rolled edge (mill edge) steel plate.
6. This table also applies to CSC ACR-TEN .

### 7.2.13 The Applicable Size Ranges of ASTM A6,A568 and A635

Unit : mm

Thickness (t)	Width (w)	720 ≤ w < 1220	1220 ≤ w ≤ 1650
1.2 ≤ t < 4.58	coil : A568 sheet : A568		coil : A635 plate : A6
4.58 ≤ t < 5.85			
5.85 ≤ t ≤ 12.7			

Remark : 1. A568 applies to A1011 specifications.

2. A635 applies to the heavy thickness coils of A1011, A1018 specifications.

3. A6 applies to A36 and A1011,A1018 specifications.

### 7.2.14 ASTM A568 Thickness Tolerances of Hot-Rolled Steel Sheets and Coils (Carbon Steel) Unit : mm

Thickness (t) \ Width(w)	$508 \leq w < 1016$	$1016 \leq w < 1220$	$1220 \leq w < 1524$	$1524 \leq w < 1829$	$1829 \leq w$
$1.2 \leq t < 1.30$	$\pm 0.10$	$\pm 0.10$	—	—	—
$1.30 \leq t < 1.45$	$\pm 0.10$	$\pm 0.11$	$\pm 0.11$	$\pm 0.12$	—
$1.45 \leq t < 1.81$	$\pm 0.11$	$\pm 0.11$	$\pm 0.12$	$\pm 0.12$	—
$1.81 \leq t < 2.49$	$\pm 0.12$	$\pm 0.12$	$\pm 0.12$	$\pm 0.15$	$\pm 0.15$
$2.49 \leq t < 4.58$	$\pm 0.12$	$\pm 0.15$	$\pm 0.15$	$\pm 0.15$	$\pm 0.15$
$4.58 \leq t \leq 5.84$	$\pm 0.15$	$\pm 0.17$	$\pm 0.19$	$\pm 0.20$	$\pm 0.22$

Remark 1. The above table applies to ASTM A1011 specifications.

2. The values in the above table are converted from inch-pound units.

3. Thickness shall be measured at any point across the width not less than 9.5mm from a cut edge and not less than 19mm from a mill edge.

4. The above table does not apply to the uncropped ends of mill-edged coils.

### 7.2.15 ASTM A568 Thickness Tolerances of Hot-Rolled Steel Sheets and Coils (High-Strength Low-Alloy Steel) Unit : mm

Thickness (t) \ Width(w)	$509 \leq w < 813$	$813 \leq w < 1017$	$1017 \leq w < 1220$	$1220 \leq w < 1525$	$1525 \leq w < 1830$	$1830 \leq w \leq 2032$
$1.20 \leq t < 1.30$	$\pm 0.11$	$\pm 0.11$	$\pm 0.11$	—	—	—
$1.30 \leq t < 1.50$	$\pm 0.11$	$\pm 0.11$	$\pm 0.12$	$\pm 0.12$	—	—
$1.50 \leq t < 1.78$	$\pm 0.12$	$\pm 0.12$	$\pm 0.12$	$\pm 0.12$	$\pm 0.15$	—
$1.78 \leq t < 2.09$	$\pm 0.12$	$\pm 0.12$	$\pm 0.12$	$\pm 0.12$	$\pm 0.15$	$\pm 0.15$
$2.09 \leq t < 2.49$	$\pm 0.12$	$\pm 0.15$	$\pm 0.15$	$\pm 0.15$	$\pm 0.17$	$\pm 0.17$
$2.49 \leq t < 4.58$	$\pm 0.15$	$\pm 0.15$	$\pm 0.19$	$\pm 0.19$	$\pm 0.20$	$\pm 0.22$
$4.58 \leq t \leq 5.84$	$\pm 0.17$	$\pm 0.17$	$\pm 0.19$	$\pm 0.19$	$\pm 0.20$	$\pm 0.22$

Remark : 1. The above table applies to ASTM A1011 specifications.

2. The values in the above table are converted from inch-pound units.

3. Thickness shall be measured at any point across the width not less than 9.5mm from a cut edge and not less than 19mm from a mill edge.

4. The above table does not apply to the uncropped ends of mill-edged coils.

### 7.2.16 ASTM A568 Width Tolerances of Hot-Rolled Steel Sheets and Coils

Unit : mm

Width (w)	Tolerance			
	Mill edge		Cut Edge	
	Carbon Steel	High-Strength Low-Alloy Steel		
720 ≤ w < 763	+ 23 0	+ 28 0	+ 3.1 0	
763 ≤ w < 890	+ 28 0	+ 28 0	+ 4.7 0	
890 ≤ w < 1220	+ 28 0	+ 31 0	+ 4.7 0	
1220 ≤ w < 1270	+ 28 0	+ 31 0	+ 6.3 0	
1270 ≤ w < 1525	+ 38 0	+ 38 0	+ 6.3 0	
1525 ≤ w < 1651	+ 38 0	+ 41 0	+ 7.9 0	
1651 ≤ w < 1778	+ 38 0	+ 44 0	+ 7.9 0	
1778 ≤ w ≤ 1981	+ 38 0	+ 47 0	+ 7.9 0	

Remark : 1. The above table applies to ASTM A1011 specifications.

2. The values in the above table are converted from inch-pound units.

3. The above table does not apply to the uncropped ends of mill-edged coils.

### 7.2.17 ASTM A568 Length Tolerances of Hot-Rolled Steel Sheets

Unit : mm

Length (L)	763 ≤ L < 1525	1525 ≤ L < 3049	3049 ≤ L < 3963	3963 ≤ L < 4877	4877 ≤ L < 6096	6096 ≤ L
Tolerance	+ 12.7 0	+ 19.0 0	+ 25.4 0	+ 31.7 0	+ 38.1 0	+ 44.4 0

Remark : 1. The above table applies to A1011 specifications.

2. The values in the above table are converted from inch-pound units.

### 7.2.18 ASTM A635 Thickness Tolerances of Hot-Rolled Steel Sheets

Unit : mm

Width (w) Thickness (t)	509 ≤ w < 1017	1017 ≤ w < 1220	1220 ≤ w < 1525	1525 ≤ w < 1830	1830 ≤ w
5.84 ≤ t < 7.96	±0.20	±0.22	±0.22	±0.25	±0.27
7.96 ≤ t < 9.53	±0.22	±0.25	±0.26	±0.27	±0.30
9.53 ≤ t ≤ 12.7	±0.26	±0.26	±0.27	±0.30	±0.34

Remark : 1. The above table applies to ASTM A1011 and A1018 specifications.

2. The values in the above table are converted from inch-pound units.

3. Thickness shall be measured at any point across the width not less than 15.875 mm from a cut-edge and not less than 25.4 mm from a mill-edge.

4. The above table does not apply to the uncropped ends of mill-edged coils.

### 7.2.19 ASTM A635 Width Tolerances of Hot-Rolled Heavy-Thickness Carbon Steel Coils Unit : mm

Width (w)	Tolerance	
	Mill Edge	Cut Edge
$720 \leq w < 763$	+ 28	+ 3.1 0
	0	
$763 \leq w < 890$		+ 4.7 0
$890 \leq w < 1220$	+ 31	
	0	
$1220 \leq w < 1271$		+ 6.3 0
$1271 \leq w < 1525$	+ 38	
	0	
$1525 \leq w < 1652$	+ 41	
	0	
$1652 \leq w < 1779$	+ 44	+ 7.9 0
	0	
$1779 \leq w \leq 2032$	+ 47	
	0	

Remark : 1. The above table applies to A1011 and A1018 specifications.

2. The values in the above table are converted from inch-pound units.

3. The above table does not apply to the uncropped ends of mill-edged coils.

### 7.2.20 ASTM A36 Thickness Tolerances of Hot-Rolled Steel Plates Unit : mm

Thickness (t)	Width (w)	7 2 0 $\leq$ w $\leq$ 2 1 3 2	
		+ 0.76	- 0.25
$t \leq 25.4$			

Remark : 1. The above table applies to ASTM A36 and A1011 specifications.

2. The values in the above table are converted from inch-pound units-

3. Thickness shall be measured at any point across the width 9.5 to 20 mm from the longitudinal edge .

4. For thickness measured at any location other than that specified in remark 3, the permissible maximum over tolerance shall be increased by 75%.

### 7.2.21 ASTM A6 Width and Length Tolerances of Hot-Rolled Steel Plates

Unit : mm

Length (L)	Width (w)	Width Tolerance		Length Tolerance	
		Mill Edge	Cut Edge		t < 9.53
			t < 9.53	9.53 ≤ t ≤ 15.87	
762 ≤ L < 3048	720 ≤ w < 889	+ 28 0	+ 9 - 6	+ 11 - 6	+ 12 - 6
	889 ≤ w < 1270	+ 31 0			
	1270 ≤ w < 1524	+ 38 0			
	1524 ≤ w < 1651	+ 41 0	+ 11 - 6	+ 12 - 6	+ 15 - 6
	1651 ≤ w < 1778	+ 44 0			
	1778 ≤ w ≤ 2031	+ 47 0			
3048 ≤ L < 6096	720 ≤ w < 889	+ 28 0	+ 9 - 6	+ 12 - 6	+ 19 - 6
	889 ≤ w < 1270	+ 31 0			
	1270 ≤ w < 1524	+ 38 0			
	1524 ≤ w < 1651	+ 41 0	+ 12 - 6	+ 15 - 6	+ 22 - 6
	1651 ≤ w < 1778	+ 44 0			
	1778 ≤ w ≤ 2031	+ 47 0			
6096 ≤ L ≤ 7620	720 ≤ w < 889	+ 28 0	+ 9 - 6	+ 12 - 6	+ 25 - 6
	889 ≤ w < 1270	+ 31 0			
	1270 ≤ w < 1524	+ 38 0			
	1524 ≤ w < 1651	+ 41 0	+ 12 - 6	+ 15 - 6	+ 28 - 6
	1651 ≤ w < 1778	+ 44 0			
	1778 ≤ w ≤ 2031	+ 47 0			

Remark : 1. The above table applies to ASTM A36 specification.

2. The values in the above table are converted from inch-pound units.

3. " t " is the thickness of material.

# 8

## 8.1 Product Types and Mass Range

Item	Product Type	Mass Range
Plate and Sheet	HR Plate and Sheet, Mill Edge	2.0 ~5.0t / Pack
	HR Plate and Sheet, Cut Edge <sup>(1)</sup>	
Coil	HR Coil, Mill edge	6.0~33t / Coil
	HR Coil, Pickled and Oiled, Mill Edge	5.3~30t / Coil
	HR Coil, Pickled and Oiled, Cut Edge <sup>(1)</sup>	5.3~30t / Coil
	HR Coil, Pickled and Annealed-Spheroidized, Cut Edge	5.3~30t / Coil
	HR Coil, Pickled and Annealed, Cut Edge	5.3~30t / Coil
	HR Band	6.0~33t / Coil

Note 1 : These product types will be produced when a customer has no special requirements.

## 8.2 Available Sizes

Unit : mm

HR Product	Thickness Range	Mill Edge	Cut Edge	Length Range/Inside Diameter
Sheet	1.20~5.99	—	860~1545	760~6096
Plate	6.00~12.7		860~1524	1500~7620
Coil	1.20~6.50	720~1855	—	Inside Diameter 762
	6.51~7.99	850~1560		
	8.00~9.50	850~1250		
Pickled and Oiled Coil	1.30~6.50	760~1575	785~1575	Inside Diameter 610
Band	2.00~10.0	740~1855	—	Inside Diameter 762
	10.01~20.0	740~1560		
Pickled and Annealed	2.00~6.50	—	785~1550	Inside Diameter 610
Pickled and Annealed-Spheroidized	2.00~6.50	—	785~1550	Inside Diameter 610

Note : The table as a reference only.

### 9.1 Marking for Hot Rolled steel



Marking Item	1	2	3	4	5	6	7	8	9	10
CSC logo	CSC name	Product name	Specification	Size	Identification	Net mass	Gross mass	Edge type	Heat no	

### 9.2 Packing for Hot Rolled steel

Hot rolled coil		Hot rolled PO coil		Hot rolled sheet	
1	Circumference Strapping	1	Inside Circumference Strapping	1	Plastic Film
2	Eye Strapping	2	VCI Paper	2	Transversal Strapping
3	Plastic Edge Protector	3	Sheet Metal Protector (circumferential surface)	3	Plastic Edge Protector
		4	Sheet Metal Protector (side wall)		
		5	Sheet Metal Protector (inner surface)		
		6	Metal Edge Protector (outside diameter)		
		7	Metal Edge Protector (inside diameter)		
		8	Outside Circumference Strapping		
		9	Outside Eye Strapping		

# 10



## 10.1 Surface Quality Control

The surface quality controls for hot rolled products when producing are based on the requirements of downstream uses. Such controls are roughly classified as Un-Exposed (UE), General Purposes (GP), and General Exposed (GE), as shown in Table 1.

Table 1. Hot rolled surface, quality and suitable applications recommended

Class	GE (General Exposed)	GP (General Purposes)	UE (Unexposed)
Application	Bicycle Parts, Elevator Panel, Brake Backing Plate, ERW Pipe for Electro-coating, Ceiling Fan Parts, Jack (electrostatic coated), Automobile Backing Parts, Oil Drum Nozzle Motorcycle,Sprocket(Cr-Coating), Wheel Disk and Wheel Rim (Electrical Galvanized or Electrostatic Coated), Bumpers.	Bicycle Gear Hanger,Jack, Square Pipe Compressor Case, Motorcycle Tube, Drawing Tube, Tubes for Automobile Cushion, Automobile Parts, Automobile Rear Axle, Drive Shaft, Boiler Parts Water Stop of Slurry Wall For LNG Tank Oil Drum, Oil Tank, Gardening Tool, Gas Cylinder, Hand Tool -SxxC, Cold Re-Rolling, Warehouse, Non-Expanded Welded Line Pipe, Speaker Washer Free Wheel For Motorcycle, Bicycle Tube ,Container Trailer Chassis, Container Locking Rod , Wheel Disk or Wheel Rim ( For Painting )	Container Angle Plate Tubes For Structural Use Chain Plate Black or Hot-Dipped ERW Pipe Chain Retaining Wall Spiral Pipe Fence Parts Guardrail of Highway Dust Tube for Thermal Power Plant Chain Plate(Re-Rolling)

## 10.2 Hardness profile along steel strip

After rolling and coiling, hot rolling strip will be gradually cooling down under room temperature. Due to the cooling rate of coil outer side is faster than inner side, the hardness of head and tail will be a fraction harder. Along the width direction, side part will be a fraction harder than central part.

## 10.3 Formability

Formability is based on hardness, metallographic structure, cleanliness of the steel. Furthermore, most steel are prone to orientation, such as bending work, cracking will happen more when bending axis is parallel with coil rolling direction (longitude direction). On the other hand, bending work will be more successful when bending axis is vertical with longitude direction. Common physical characteristics of mechanical property and influence on formability of steel are listed in Table 2.

Table 2. Common physical characteristics of mechanical property and influence on formability of steel

Item	Physical characteristics	Influence
Yield Strength	Difficulty to do plastic deformation	YS ↓ Formability ↑
Tensile Strength	Difficulty for cracking happen	—
Elongation	The elongation from deformation to cracking	EL ↑ Formability ↑
Yield ratio	Difficulty to do working and rebounding	YS/TS ↓ Formability ↑
Hardness	Hardness of steel strip	HR ↓ Formability ↑ (not absolutely)

## 10.4 Classification and Purpose of quality

Table 3. List of classification, specification, property and purpose of hot-rolled product.

Classification	Common Specification	Property and purpose
Commercial Quality(CQ)	JIS G3131 SPHC SAE 1008~1023 CQ	Appropriate for normal forming, bending, welding, such as water pipe, electric wire pipe, parts with non strength demand, cover...etc.
Drawing Quality(DQ)	JIS G3131 SPHD JSH 270D 270E SAE 1006~1008 DQ	Appropriate for drawing work or forming, such as bicycle bead, handle grip, 5-way pipe...etc.
Structure Quality(SQ)	SS400、SS490 SM400、SM490 ASTM A36	Appropriate for simple bending work, welding and rivet joint with strength demand, such as ship hull, bridge, scaffold...etc.
Automobile Structure Quality(ASQ)	JIS G3113 SAPH310、 SAPH370、SAPH400、 SAPH440、SPFH590、 CSC HM690T、JSH780R	Appropriate for automobile parts, with strict inner quality and forming demand, normally used for automobile wheel rim, suspension system, chassis beam, brake back panel...etc.
Corrosion Resistance Steel Quality(CRSQ)	JIS G3125 SPA-H， CSC ACR-TEN A、ACR-TEN AF	Adding elements like Cu, Cr, P, makes steel forming protective oxidizing firm, to avoid corrosion. Commonly used for container, rail car, bridge...etc.
Pressure Vessel Quality(PVQ)	JIS G3116 SG255、SG295 ASTM A516 GR60、70	Emphasizes strength, welding, formability, and strict inner quality. Some demand low toughness. Commonly used for steel gas cylinder and other pressure vessel.
Line Pipe Steel(LPS)	API 5LB、API X42、X52、X60， JIS G3132 SPHT1、SPHT2、 SPHT3、SPHT4	Strength, low temperature toughness, welding, formability, inner quality are all strictly demanded. Mainly used for gasoline, gas vapor, liquid transportation.
Mechanical Structure Quality(MSQ)	JIS S35C、S45C、S50C、 SCM415~SCM435， SAE 4130、1552	When such steel is manufactured as parts, it needs to do some heat treatment such as annealing, quenching, tempering by property, to raise and stabilize strength and hardness of the parts. Commonly used for gardening tool, chain plate, hand pull device...etc.
Re-Rolling Quality(RRQ)	SAE1006 RRQ ~ SAE1022 RRQ	Such steel is designed according to customer quality demand and process ability. It can be produced to cold rolling steel, galvanizing steel, color steel.

## 10.5 Common steel grade classify by strength

Common HR steel grade classify by strength is as Table 4.

Table 4. Common HR steel grade classify by strength

T.S. (kg/mm <sup>2</sup> )	30	35	40	45	50/55	60
Commercial Quality (CQ)	SPHC SAE1006 CQ SAE1008 CQ SAE1010 CQ ASTM A569	SAE1012	SAE1015~ SAE1019	SAE1020~ SAE1023	SAE1025	
Drawing Quality (DQ)	SPHD、 SPHE JSH270D SAE1006 DQ SAE1008 DQ ASTM A621					
Structure Quality (SQ)	SAE1010 CQ SPHT1	SPHT2 SS330 A470 GR30 A570 GR33 A570 GR36	SPHT3 SS400 SM400 ASTM A36 A570 GR40 A570 GR45	A570 GR50 A570 GR55	SPHT4 SS490 SS540 SM490A SM490YA	
Automobile Structure Quality (ASQ)	SAPH310	SAPH370	SAPH400	SAPH440	SPFH540	SPFH590
Corrosion Resistance Steel Quality (CRSQ)			ACR-TEN AF		ACR-TEN A SPA-H	
Pressure Vessel Quality (PVQ)			SG255	SG295	SG325、 365	
Line Pipe Steel (LPS)		API 5L GRA	API 5L GRB API 5L X42	API 5L X46	API 5L X52 API 5L X56	API 5L X60 API 5L X65
Re-Rolling Quality (RRQ)	SAE1006 RRQ SAE1010 RRQ	SAE1012 RRQ	SAE1017 RRQ		S35C RRQ S40C RRQ	S45C RRQ S50C RRQ
Mechanical Structure Quality (MSQ)					S35C S40C S45C	SAE1045~ 1060 S45C、 S50C SAE4130

## 10.6 Quality Notification

- (1) HR red rust (Tiger Mark) – When HR product have Si above 0.08%, there will be red rust (Tiger Mark) on the surface.  
Consider some grinding treatment before using.
- (2) Selection of thickness tolerance – Attention should be given to cut edge or mill edge. Though it match ordering spec tolerance, thinner side parts will still influence usage.
- (3) Damp caused by huge temperature difference (rust caused by fog) – Non-packing steel should watch out its storage environment and temperature variation, to avoid moisture.

## 10.7 Potential Safety Hazards

- (1) If the sides of HR products have rough or saw edge, they will have the potential dangers of scratching hands.
- (2) If the shapes of HR coils are not good, they will have the potential dangers of falling down when lifting or storing.
- (3) If HR products have defects such as sliver, lamination or hole, they will have the potential dangers of strip break to collide with machine or hurt people when slitting to make pipes or re-rolling.
- (4) HR product has potential dangers of break.
- (5) If oiled HR plates are not packed with steel straps, they will have the potential dangers of falling down when lifting or storing.
- (6) It will have the potential dangers of springing open to hurt people when their steel straps are being cut.

# CONVERSION TABLES

# 11

	ft	inch	mm	m
Length	1	12	$3.048 \times 10^2$	$3.048 \times 10^{-1}$
	$8.333 \times 10^{-2}$	1	$2.54 \times 10^1$	$2.54 \times 10^{-2}$
	$3.281 \times 10^{-3}$	$3.937 \times 10^{-2}$	1	$1 \times 10^3$
Mass	$1\text{kg} = 2.20462 \text{ lb}$			
Force	$1\text{kgf} = 9.80665 \text{ N}$			
	ksi (=1000psi)	psi	kgf/mm <sup>2</sup>	N/mm <sup>2</sup> (=MPa)
Stress	1	$1 \times 10^3$	$7.0307 \times 10^{-1}$	6.89476
	$1 \times 10^{-3}$	1	$7.0307 \times 10^{-4}$	$6.89476 \times 10^{-3}$
	1.42233	$1.42233 \times 10^3$	1	9.80665
	$1.45038 \times 10^{-1}$	$1.45038 \times 10^2$	$1.01972 \times 10^{-1}$	1
	ft-lbf	kgf-m	N-m (J)	
Absorbed Energy	1	$1.38255 \times 10^{-1}$	1.35582	
	7.23301	1	9.80665	
	$7.37562 \times 10^{-1}$	$1.01972 \times 10^{-1}$	1	

# 12

Steel Type	JIS	JFS	EN	ASTM	SAE
Commercial and drawing steel	CQ	G3131 SPHC	A1001 JSH270C	10111 DD11	A1011 CS
	DQ	G3131 SPHD	A1001 JSH270D	10111 DD12	A1011 DS
	DDQ	G3131 SPHE	A1001 JSH270E	10111 DD13	—
	EDDQ	G3131 SPHF	—	10111 DD14	—
Atmospheric Corrosion Resisting Steel	G3125 SPA-H	—	10155 S355J2WP	A242	—
Steel for Gas Cylinders	G3116 SG295	—	10120 P265NB	A414 Gr. B	—
Steel for General Structure	G3101 SS400	—	10025 S235J	A36	—
High Strength Steel for Automobile Structural Uses	G3134 SPFH490~590	A1001 JSH490~590R/W	10149 S420MC~S550MC	—	J2340 420~550XF
Carbon Steel	G4051 S22C~S55C	—	10083-1 C22E~C55E	—	J403 1022~1050
Cr-Mo Steel	G4053 SCM425~ SCM440	—	10083-1 25CrMo4~42CrMo4	—	J404 4130~4140

Note : Not equal between different steel grades, the above table is a comparison table for reference only.

# 13

For prompt and proper processing of your inquiries and orders, please furnish complete details of items as shown in the box below.

Required Ordering Data				Example		
1	Product Name	HR Plate	HR Pickled and Annealed/A annealed-Spheroidized Coil	HR Coil		
		HR Sheet	HR Pickled and Oiled Coil			
		HR Coil	HR Band			
2	Specification and Designation of Grade			JIS G3131 SPHC		
3	Cut Edge or Mill Edge			Mill Edge		
4	Size (Thickness × width × Length or Coil)			1.60mm×1219mm×Coil		
5	Inside and Outside Diameter			ID 762mm · OD 1700mm max.		
6	Mass	Maximum Mass		10t		
		Order Mass		150t		
7	Application and Fabricating Methods			Bicycle parts		
8	Special Requirements(if Required)			—		

- (1) The contents of this catalog are for reference only. Customers are urged to consult the specifications published by the corresponding Associations.
- (2) Information on the available steel grades, size, marking and packing as shown herein may be updated without notice to comply with actual production situations.
- (3) We invite you to contact our Head Office should you have any questions concerning steel specifications or ordering requirements.

**Phone number are listed below for your convenience. Numbers of our international Offices are shown on the back cover.**

## 1.Sales services

### CHINA STEEL GLOBAL TRADING CORPORATION

| Address: 10F, NO.88, Cheng gong 2nd Rd, Qian zhen, Kaohsiung 80661 TAIWAN  
| Tel : 886-7-3322168 | Fax : 886-7-3356411 | E-mail : c00681@mail.csc.com.tw

### CSGT JAPAN CO., LTD.

| Address: 2F, Osaka U2 Bldg., 4-7 Uchihonmachi 2-Chome, Chuoku, Osaka 540-0026, Japan  
| Tel : 002-81-6-69100850 | Fax : 002-81-6-69100851 | E-mail : gdwu@csgtjpn.co.jp

### CSSGT HONG KONG LIMITED

| Address : ROOM 1407,14/F, WORLD WIDE HOUSE, 19 DES VOEUX ROAD, CENTRAL, HONG KONG  
| Tel : 852-25231488 | Fax : 852-25234748 | E-mail : mhliu@csgthk.com.hk

### CSSGT (SHANGHAI) CO.,LTD.

| Address : 21F, NO.1468 NAN JING WEST RD., SHANGHAI 200040  
| Tel : 86-21-62896898 | Fax : 86-21-62896678 | E-mail : c00392@csgtsha.com

### CSSGT (SINGAPORE) PTE, LTD.

| Address : # 14-01, MAS BUILDING, 10 SHENTON WAY SINGAPORE 079117  
| Tel : 65-62238777~8 | Fax : 65-62256054 | E-mail : changcc@csgtsg.com.sg

## 2.Metallurgical Department

Technical Service Section-Metallurgy: 886-7-8021335

Metallurgical Specification and Testing Section: 886-7-8021111 Ext. 3261



### **Head Office**

- Address : #1, Chung Kang Rd., Hsiao Kang, Kaohsiung 81233, Taiwan, Republic of China
- Tel : 886-7-802-1111
- Fax : 886-7-802-2511 , 801-9427
- Web : <http://www.csc.com.tw>

### **China Steel Building** (Group Headquarters)

- Address : #88, Chenggong 2nd Rd., Qianzhen, Kaohsiung 80661, Taiwan, Republic of China
- Tel : 886-7-337-1111
- Fax : 886-7-537-3570

### **Taipei Liaison Office**

- Address : Room A, 28F, #7, Sec.5, Xinyi Rd., Xinyi, Taipei 11049, Taiwan, Republic of China
- Tel : 886-2-8758-0000
- Fax : 886-2-8758-0007

(Manual download)



### **Osaka Office**

- Address : 1F, Osaka U2 Bldg., 4-7Uchihonmachi 2-Chome, Chuoku , Osaka 540-0026, Japan.
- Tel : 81-6-6910-0888
- Fax : 81-6-6910-0887

### **Singapore Office**

- Address : # 14-01 Mas Building, 10 Shenton Way, Singapore 079117
- Tel : 65-6223-8777-8
- Fax : 65-62256054



CAT.NO.3-HR-01-2014-E1